

# S.C. AGP VECTORIAL S.R.L.

St. Dezrobirii Nr.27, Craiova, Romania

Phone/Fax: +40351809394

Email: [agp\\_vectorial@yahoo.com](mailto:agp_vectorial@yahoo.com)

[www.agpvectorial.ro](http://www.agpvectorial.ro)



## POSITIVE PS PLATE-Technical Data Sheet

**Product scale:** Thickness 0.15-0.40mm, width≤1600mm

**Aluminum alloy:** International standard 1050 alloy

**Photosensitive spectrum:** 320-450nm

**Resolution:** 8-10um2-98%

**Coating color:** Blue

**Baking:**200~250°C,5~8min

**Run length:** 60000-80000

**Storage period:** 18 months

**Storage condition:** Temperature:10-30°C, humidity<65%, stacking height<1.5m,avoid light,moisture-proof,heat insulation, antifreeze, far away from other chemicals

**Processing condition:**

***-Exposure condition:***

Light 3kw  
Distance 1meter  
Time 70-80secs

***-Developing condition:***

Developer dilute ratio 1:4(machine)-1:6(hand)  
Developing powder ratio 1:20(machine)-1:16(hand)  
Developing Temperature 23-25°C  
Developing Time 20-30secs